


Epona Z 100

Mineral oils for enclosed gears.



APPLICATIONS

Enclosed gears, bearings, couplings.

Bevel and spur gears.

Bearings and gear couplings.

Worm gears.

FEATURES AND BENEFITS

Epona Z 100 has been specially designed for lubricating enclosed gears operating under severe conditions.

Excellent extreme-pressure and anti-wear properties.

Perfect seal compatibility.

| SPECIFICATIONS AND APPROVALS | | | | |
|------------------------------|-------------------------------|---|---------------------------|--|
| ~ | DIN 51517/3 - CLP | ~ | JIS K2219. 2006 (Class 2) | |
| ~ | ISO 12925-1 CKSMP | ~ | David Brown S1.53.101 E | |
| ~ | AGMA 9005 - F 16 Antiscuffing | | | |

| TECHNICAL DATA: EPONA Z 100 | | | | | |
|-----------------------------|--------------|------------|-----------------|--|--|
| CHARACTERISTICS | METHODS | UNITS | TYPICAL VALUES* | | |
| Density at 15°C | ISO 3675 | kg/m³ | 882 | | |
| Viscosity at 40°C | ISO 3104 | mm²/s | 100 | | |
| Viscosity at 100°C | ISO 3104 | mm²/s | 11.3 | | |
| Viscosity Index | ISO 2909 | _ | 98 | | |
| Pour Point | ISO 3016 | °C | - 27 | | |
| Flash Point (OC) | ISO 2952 | °C | 222 | | |
| FZG Micropitting | FVA 54 | Fail stage | 10 high | | |
| FZG A/8.3/90 | DIN 51 354/2 | Fail stage | 14 pass | | |
| GFT Class | - | _ | _ | | |

^{*}The specifications above are for illustrative purposes and communicated for information only.





| CUSTOMER BENEFITS | | | |
|-------------------|---|--|--|
| V | Excellent chemical stability and resistance to oxidation, for a long period of running without maintenance. | | |
| ~ | Oustanding protection to rust and corrosion of copper alloys. | | |
| ~ | Very good resistance to foaming and emulsion formation. | | |

GENERAL RECOMMENDATIONS

COMPATIBILITY

Compatibility should be checked.

Please consult your Marine Lubrication Engineer should you have any questions.

STORAGE

This product should be stored under cover in clean, dry conditions and protected from frost.

Recommended storage temperature range is 5°C to 50°C.

Drums that are stored on deck should be raised on pallets and covered to protect from the elements.

| COMPLIMENTARY PRODUCTS AND SERVICES | | | | |
|-------------------------------------|--|--|--|--|
| ~ | LubDiag – Oil Analysis – Laboratory based used oil analysis program. | | | |
| ~ | LubInsight – Suite of onboard testing equipment. | | | |
| ~ | LubSkills – Lubmarine Engineers are on hand at worldwide locations to assist with lubrication concerns. | | | |
| / | Lub On Ship – Visualize your lubricants needs aboard Lubmarine's innovative virtual vessel. lubmarine.totalenergies.com/lube-on-ship | | | |





