PLANETELF ACD



Compressor



Synthetic polyolester oils for refrigerating compressors using HFC refrigerants.

UTILISATIONS									
Refrigerating compressors using HFC refrigerants									
SPECIFICATIONS									
International classification OEMs	 ISO 6743-3: DRD AERZEN, BOCK, FRASCOLD, GRAM, GRASSO, HOWDEN, MCQUAY, SABROE, SULZER, YORK. 								
ADVANTAGES									
Protects the different components of the refrigerating loop	 ASHRAE thermal stability tests confirm the excellent behavior of the lubricant at high temperature in presence of refrigerant, water and metallic components. Neutral behaviour with the refrigerating equipments (Anti-rust, anti-corrosion properties with copper metals, compatibility with varnishes, elastomers and paints, high resistance to hydrolysis) 								
Enhances the efficiency of the refrigerating equipment	 Low dilution of refrigerant in oil for the high viscosity grades (PLANETELF ACD FY range), for good lubricity and oil separation properties (low carry-over) The good miscibility of the fluid viscosities of PLANETELF ACD allows a good oil return property, specially in dry-ex equipments. 								
TYPICAL CHARACTERISTICS	METHODS	UNITS	PLANETELF ACD						
			32	46	68	100FY	150FY	220FY	
Density at 15°C	ISO 3675	kg/m ³	981	971	962	958	991	1019	
Kinematic viscosity at 40°C	ISO 3101	mm²/s	32	46	68	100	150	220	

Kinematic viscosity at 40°C	ISO 3101	mm²/s	32	46	68	100	150	220
Kinematic viscosity at 100°C	ISO 3101	mm²/s	6.0	7.5	9.1	11	15.5	20.8
Pour Point	ISO 3116	°C	-54	-45	-39	-33	-33	-33
Flash point (COC)	ISO 2592	°C	250	250	250	268	264	264
Acid number	ASTM D 974	mgKOH/g	<0.1	<0.1	<0.1	<0.1	<0.15	<0.2
Water content	KARL FISHER	ppm	<50	<50	<50	<50	<100	<100
Above characteristics are mean values given as an information								

Above characteristics are mean values given as an information.

The miscibility and viscosity curves are available upon request.

TOTAL LUBRIFIANTS INDUSTRIE 17-10-2017 (supersedes 23-07-2009) PLANETELF ACD 1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or down loaded from <u>www.quick-fds.com</u>.